CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 16/06/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-05-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	16/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	151.92 X 149.87 X 150.58	22769	8.586	632.4	27.8	27.5
2	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	151.09 X 149.32 X 151.09	22560	8.206	598.0	26.5	
3	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	151.52 X 150.85 X 151.83	22857	8.245	648.1	28.4	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-31-86** **Date: 26/05/2019**

Customer : Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.

Address : T-Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15

Agency : Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.

Customer's Reference : EE/SWD/DHZ/WO/06/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-05-19

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 26/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	150.25 X 151.96 X 151.95	22832	8.572	537.2	23.5	23.0
2	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	149.83 X 149.59 X 149.48	22414	8.136	513.5	22.9	
3	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	151.15 X 151.74 X 150.46	22937	8.791	520.0	22.7	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : CP-2020-01-31-86 **Date: 16/06/2019**

Customer : Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.

Address : T-Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15

Agency : Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.

Customer's Reference : EE/SWD/DHZ/WO/06/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-05-19

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 16/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	151.64 X 150.79 X 150.17	22866	8.586	630.9	27.6	27.4
2	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	151.00 X 151.49 X 151.62	22874	8.206	609.1	26.6	
3	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	151.62 X 149.10 X 149.41	22607	8.245	634.5	28.1	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 26/05/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-05-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	26/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	149.82 X 150.34 X 150.56	22524	8.572	535.1	23.8	22.8
2	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	149.38 X 150.30 X 150.83	22453	8.136	507.0	22.6	
3	Drain Side Wall Concrete	M25	19/05/2019	26/05/2019	151.94 X 149.30 X 150.76	22685	8.791	501.6	22.1	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 16/06/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-05-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	16/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	151.49 X 149.36 X 151.46	22627	8.586	623.6	27.6	27.6
2	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	149.44 X 151.18 X 150.53	22592	8.206	608.0	26.9	
3	Drain Side Wall Concrete	M25	19/05/2019	16/06/2019	150.70 X 150.19 X 150.30	22634	8.245	640.1	28.3	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 28/05/2019

Lab ID	:	**CP-2020-01-31-86**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	23-05-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	28/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M25	21/05/2019	28/05/2019	151.48 X 150.42 X 149.98	22787	8.572	546.0	24.0	23.0
2	Drain Side Wall Concrete	M25	21/05/2019	28/05/2019	151.19 X 151.94 X 151.70	22972	8.136	521.1	22.7	
3	Drain Side Wall Concrete	M25	21/05/2019	28/05/2019	151.67 X 150.04 X 151.98	22757	8.791	506.1	22.2	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

ಸಹಾಯಕ ಕಾರ್ಯನಿರ್ವಾಹಕ ಅಭಿಯಂತರರು
ಬೃಹತ್ ಮಳೆ ನೀರುಗಾಲುವೆ ಉಪ-ವಿಭಾಗ,
ದಾಸರಹಳ್ಳಿ ವಲಯ, ಬಿ.ಬಿ.ಎಂ.ಪಿ. ಬೆಂಗಳೂರು

Page 1/1
****End of Report****

Scanned with CamScanner

CIVIL PRO

AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No. TC-6648

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID	:	**CP/2020-01-31/86** **Date: 18/06/2019**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD 6 Ramesh Road Usha School in Dasarahalli ward No.15
Agency	:	Smt K Jayamma, #11 No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	23-05-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete CL5

Date of test : 18/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M25	21/05/2019	18/06/2019	151.97 X 149.78 X 149.39	22761	8.586	622.7	27.4	27.3
2	Drain Side Wall Concrete	M25	21/05/2019	18/06/2019	150.18 X 151.03 X 150.65	22681	8.206	598.2	26.4	
3	Drain Side Wall Concrete	M25	21/05/2019	18/06/2019	151.32 X 150.41 X 150.11	22891	8.245	648.0	28.3	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative.
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate.

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorised Signatory
Quality Manager

****End of Report****

M 9972924526 | Tel +91 80 23444801 | e rechan66.30@yahoo.co.in civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-01-31-86** **Date: 28/05/2019**

Customer : Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.

Address : T-Dasarahalli Sub Division, BBMP, Bangalore.

Project Name : Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15

Agency : Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.

Customer's Reference : EE/SWD/DHZ/WO/06/2017-18

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 23-05-19

Customer ID : Drain Side Wall Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M25 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 28/05/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M25	21/05/2019	28/05/2019	149.76 X 151.11 X 151.37	22630	8.572	523.9	23.2	22.7
2	Drain Side Wall Concrete	M25	21/05/2019	28/05/2019	149.67 X 149.35 X 151.47	22352	8.136	509.4	22.8	
3	Drain Side Wall Concrete	M25	21/05/2019	28/05/2019	150.50 X 149.49 X 151.55	22498	8.791	496.5	22.1	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

CIVIL PRO

AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 18/06/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	23-05-19
Customer ID	:	Drain Side Wall Concrete
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M25 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	18/06/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Drain Side Wall Concrete	M25	21/05/2019	18/06/2019	151.35 X 151.61 X 150.82	22946	8.586	630.8	27.5	27.5
2	Drain Side Wall Concrete	M25	21/05/2019	18/06/2019	150.77 X 149.95 X 151.49	22609	8.206	591.4	26.2	
3	Drain Side Wall Concrete	M25	21/05/2019	18/06/2019	149.47 X 149.87 X 150.21	22401	8.245	647.6	28.9	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 12/07/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-07-19
Customer ID	:	Cement Concrete pavement
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	12/07/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete pavement	M30	05/07/2019	12/07/2019	149.49 X 151.39 X 149.40	22632	8.220	582.6	25.7	25.6
2	Cement Concrete pavement	M30	05/07/2019	12/07/2019	151.71 X 149.65 X 149.13	22703	8.651	611.4	26.9	
3	Cement Concrete pavement	M30	05/07/2019	12/07/2019	150.84 X 150.45 X 150.21	22694	8.121	547.0	24.1	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Page 1/1
****End of Report****

Scanned with CamScanner

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 02/08/2019

Lab ID	:	**CP-2020-01-31-86**
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-07-19
Customer ID	:	Cement Concrete pavement
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 28 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5
Date of test	:	02/08/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete pavement	M30	05/07/2019	02/08/2019	149.54 X 151.06 X 150.10	22588	8.877	751.0	33.2	33.1
2	Cement Concrete pavement	M30	05/07/2019	02/08/2019	151.65 X 151.40 X 151.82	22960	8.080	739.6	32.2	
3	Cement Concrete pavement	M30	05/07/2019	02/08/2019	150.43 X 151.01 X 149.48	22716	8.433	770.1	33.9	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Date: 12/07/2019

Lab ID	:	CP-2020-01-31-86
Customer	:	Assistant Executive Engineer, T-Dasarahalli Sub Division, BBMP, Bangalore.
Address	:	T-Dasarahalli Sub Division, BBMP, Bangalore.
Project Name	:	Construction of RCC Culvert & U Shape Drain for Secondary SWD S Ramesh Road Urdu School in Dasarahalli ward No.15
Agency	:	Smt K.Jayamma, #H No:74, Behind Grama Panchayat Office, Sganbhog Layout, Dasanapura, Bangalore-562133.
Customer's Reference	:	EE/SWD/DHZ/WO/06/2017-18
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	08-07-19
Customer ID	:	Cement Concrete pavement
Sample Type /Size	:	150X150X150 mm
Sample grade/Age	:	M30 / 7 Days Compressive Strength
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 12/07/2019

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Cement Concrete pavement	M30	05/07/2019	12/07/2019	149.07 X 149.63 X 149.17	22305	8.220	561.6	25.2	25.3
2	Cement Concrete pavement	M30	05/07/2019	12/07/2019	149.50 X 151.55 X 150.54	22657	8.651	591.1	26.1	
3	Cement Concrete pavement	M30	05/07/2019	12/07/2019	149.38 X 149.71 X 150.89	22363	8.121	548.2	24.5	

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

R.KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com
HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Scanned with CamScanner